

Glassy transition in the vortex state of $\text{Ba}(\text{Fe}_{1-x}\text{Rh}_x)_2\text{As}_2$ superconductor as probed by high magnetic field NMR

L. Bossoni,^{1,2} P. Carretta,¹ M. Horvatić,³ M. Corti,¹ A. Thaler,⁴ P.C. Canfield⁴.

¹ *Department of Physics, University of Pavia-CNISM, I-27100 Pavia, Italy*

² *Department of Physics “E. Amaldi,” University of Roma Tre-CNISM, I-00146 Roma, Italy*

³ *Laboratoire National des Champs Magnétiques Intenses, LNCMI-CNRS (UPR3228), UJF, UPS and INSA, BP 166, 38042 Grenoble Cedex 9, France and and*

⁴ *Ames Laboratory US DOE and Department of Physics and Astronomy, Iowa State University, Ames, IA 50011, USA*

Nuclear spin-lattice relaxation rate ($1/T_1$) measurements in optimally doped $\text{Ba}(\text{Fe}_{1-x}\text{Rh}_x)_2\text{As}_2$ superconductor evidence the onset of low-frequency dynamics associated with the vortex motions. The slowing down of the dynamics yields a peak in $1/T_1$, which has been observed to progressively shift to lower temperatures as the magnetic field is increased from 3 T to 15 T. We interpreted these results in the light of a phase transition between a liquid vortex state and a glassy vortex ground-state. The Arrhenius law, employed to describe the vortex dynamics in the cuprates, fails in the case of the iron-pnictides, whereas a Vogel-Tammann-Fulcher law gives more meaningful results, together with the dynamical scaling approach. The glassy phase transition occurs below T_c , very close to the Kosterlitz-Thouless transition temperature of the vortex lattice. We further show that the anisotropy in the vortex dynamics causes also a dependence of the spin-spin relaxation rate on the magnetic field orientation.

PACS numbers: 74.25.nj, 74.25.Wx, 74.25.Uv

I. INTRODUCTION

The discovery of iron-based superconductors¹ has renewed the interest in the vortex physics. Thanks to their layered structure, the pnictides are good candidates for studying the dynamical properties of the flux line lattice. In particular the 122 family of these new superconductors can be grown in large high-quality single crystals,² suitable for nuclear magnetic resonance (NMR) experiments. On the other hand, since iron-pnictides are not as anisotropic as the cuprates or as the organic superconductors, one may wonder if the liquid vortex phase is extended enough to be investigated, and whether a transition between a liquid and a solid phase or rather a glassy-phase would occur in these novel materials.

More than 40 years ago it was argued that the material imperfections destroy the crystalline long-range order of the Abrikosov vortex lattice.³ The quenched disorder is responsible for the pinning of the vortices and for the contextual disruption of the lattice structure.⁴ After this theoretical prediction it was experimentally found^{5–8} that in the cuprates the flux-lattice melts in a glassy state occurring well below the transition temperature T_c . More recent ac-susceptibility measurements seem to evidence a glassy state in the 122 family of iron-pnictides, too⁹. Some open questions concern the possibility of observing a glassy phase transition in a 3D array of vortices, as well as the nature of such a transition: whether it is a true thermodynamic transition with a defined order parameter, or a cross-over between two regimes.¹⁰ Another issue concerns the effects of the weak anisotropy on the geometry of the vortices: whether they have to be thought as 2D vortices (pancakes) or rather proper flux tubes, and how the phase transition between 2D and 3D lattice can

be driven.

The investigation of the vortex motion is important both for the preservation of the dissipation-less properties of superconductors⁴ and for fundamental physical aspects involved. The phenomena hidden in vortex physics are extremely rich, and can respond to many experimental techniques. Apart from the pinning mechanism, provided by lattice imperfections or vacancies, there is another source of pinning, the intrinsic pinning, due to the anisotropy of these systems. In case of a layered structure, when the applied field is in the c direction, the vortices are not affected by the anisotropy in the ab plane, but when the field is applied in the ab plane, the vortex cores are located between the layers, in order to minimize their energy.¹¹ In the absence of pinning centers, vortex motion within the layers is allowed, but motion perpendicular to the layers is hindered.

Recent nuclear magnetic resonance (NMR)^{12,13} and muon spin rotation (μSR)¹⁴ measurements on iron pnictides have studied the dynamics of the flux lines lattice, but to the author's knowledge, no systematic study of both the temperature and of the magnetic field effect has been done, so far.

This paper extends our previous work (Ref. 12) where the NMR spin-lattice relaxation rate was measured at 7 T and 3 T, in a Rh-doped member of the 122 family of iron-based superconductors, near the optimally doped regime ($\text{Ba}(\text{Fe}_{1-x}\text{Rh}_x)_2\text{As}_2$, with $x \sim 0.07$). We show how the spin-lattice relaxation rate of the ^{75}As nuclei changes with temperature and field, and propose an interpretation based on a 3D flux line lattice (FLL) model, where the thermal excitations induce fluctuations perpendicular to the external magnetic field. We also notice that the Arrhenius law fails in describing the correlation

time of the vortex motion and that the Vogel-Tammann-Fulcher (VTF) law should be rather employed. This suggests the occurrence of a glassy phase transition. We discuss further on the $1/T_2$ relaxation rate measured at high field, and its dependence on the field orientation.

II. TECHNICAL ASPECTS AND EXPERIMENTAL RESULTS

The ^{75}As NMR measurements were performed on a flat $0.8 \times 5 \times 7 \text{ mm}^3$ single crystal of $\text{Ba}(\text{Fe}_{0.93}\text{Rh}_{0.07})_2\text{As}_2$ (BaFeRAs), with the c axis along the shortest side. The details about the sample are presented in Ref. 12. The earlier experiments performed on the same sample evidenced a peak in the spin-lattice relaxation rate, below the transition temperature T_c , whose position and amplitude strongly depend on the magnetic field (H) amplitude.¹² The lower field experiments ($H = 3 \text{ T}$, 7 T) are here completed with higher field ones. Experiments at $H = 8.5 \text{ T}$ were performed in Pavia, while the 11 T and 15 T experiments were carried out at the LNCMI-Grenoble. The results show remarkable similarities with an earlier study on oriented powders of the cuprate $\text{YBa}_2\text{Cu}_4\text{O}_8$ (YBCO124), with a critical temperature $\sim 81 \text{ K}$, and a higher anisotropy ratio γ .¹⁵

The NMR measurements were performed by using standard radio frequency pulse sequences. The spin-lattice relaxation time T_1 was measured by means of a saturation recovery pulse sequence and the recovery of the nuclear magnetization $m(t)$ was well fitted by a slightly stretched double exponential law, corresponding to a magnetic relaxation mechanism of a nuclear spin $I = 3/2$, for the central $(-1/2, 1/2)$ transition:

$$1 - m(t)/m_0 = 0.1 \exp(-t/T_1)^r + 0.9 \exp(-6t/T_1)^r, \quad (1)$$

with $r \rightarrow 1$. Fig. 1 shows the relaxation rate T_1^{-1} at different fields, with $\mathbf{H} \parallel c$, where a peak is observed below T_c . We immediately notice that, by increasing the field, the peak in $1/T_1$ is rapidly reduced above 7 T , so that only a small kink remains at 11 T and 15 T . As shown in Ref. 12 the peaks are visible just in $\mathbf{H} \parallel c$ geometry (Fig. 1). The contribution of the vortex dynamics to the spin-lattice relaxation rate $1/T_{1VL}$ is found by subtracting from the raw data the electronic contribution, estimated by extrapolating the data out of the peak region. This procedure is in practice equivalent to subtracting from the raw data the ones taken for $\mathbf{H} \perp c$, properly rescaled by the hyperfine factors, since for that orientation the nuclear spin-lattice relaxation is only given by the electronic spin fluctuations (Fig. 2). Namely, one has

$$\frac{1}{T_1} = \frac{1}{T_{1VL}} + \frac{1}{T_{1el}}, \quad (2)$$

where the first term is the vortex-lattice contribution, while the second one is due to electron spin fluctuations.




FIG. 1. The spin-lattice relaxation rate at different magnetic field values: 3 T (blue squares), 7 T (purple triangles), 8.5 T (green circles), 11 T (yellow stars), and 15 T (pink pentagon). All data refer to $\mathbf{H} \parallel c$ orientation. The arrows show the temperature of the detuning of the NMR probe resonating circuit.




FIG. 2. The spin-lattice relaxation rate measured at 7 T , for $\mathbf{H} \parallel c$ (black diamonds) and for $\mathbf{H} \perp c$ (blue circles), rescaled by the hyperfine coupling ratio (see Ref.12). The red dotted line is the interpolation of the data out of the peak region. The peak is visible just in the longitudinal field geometry, while in the other one, just the electronic contribution $\frac{1}{T_{1el}}$ to the nuclear spin relaxation is present. This result, already shown in Ref. 12, has been report here for the sake of clarity.

Further information on the vortex dynamics can be obtained from the spin-echo relaxation time (T_2) measurements below T_c , at 15 T . To measure T_2 we employed a Hahn-echo sequence, by varying the delay time τ between the two pulses. By defining T_2 as the time at which the echo drops at $1/e$ of its initial value, we observe a pronounced dependence of the relaxation rate on the direction of the applied field, with respect to the FeAs planes: when $\mathbf{H} \parallel c$ the spin-echo decay rate increases

with decreasing temperature. On the other hand, when $\mathbf{H} \perp c$, the rate saturates to a value in agreement with the calculation of the dipolar contribution to the relaxation following Van-Vleck summations¹² (See Fig. 3).




FIG. 3. The figure shows the spin-echo decay rate at 15 T, for $\mathbf{H} \perp c$ (red circles) and $\mathbf{H} \parallel c$ (black squares), determined by time where the echo decays to $1/e$ of its initial value.

III. DISCUSSION

Let us start our analysis with some considerations on the phase diagram of our compound. Generally, the magnetic phase diagrams for type-II superconductors are rather complex: in addition to the complete Meissner phase, a region with pinned or otherwise non-moving vortices is predicted at very low temperature, whereas at higher temperatures the FLL melts into a liquid phase, where vortices are free to move reversibly. The boundary line between the two phases is the irreversibility line, sometimes also called the melting line. Actually the irreversibility and melting do not always coincide, and Majer et al.¹⁶ showed that in $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_8$ (BSCCO) the two processes stem from different and unrelated physical mechanisms. The irreversibility line defines the boundary between irreversible and reversible motions of the vortices and should depend on the time scale of the experimental technique, as well as on the geometry of the sample, while the melting line is independent of the experiment. Above this line, the vortex cores fluctuations can be strong enough to cause the vortex solid or glass to melt into a liquid phase. When the melting occurs, according to the Lindemann criterion, the root-mean square amplitude of the vortex displacement $\langle u^2 \rangle^{1/2}$ exceeds $l_e c_L$, where l_e is the vortex lattice step and $c_L = 0.1-0.2$ is the Lindemann parameter.¹⁷ In case of a melting transition an abrupt change in the NMR quantities, a sharp peak or a step in the spin-lattice relaxation rate is expected, owing to the first-order nature of the phase transition.

Nevertheless, we didn't observe any sudden transition in the NMR relaxation times. In addition, below the temperature of the peak in $1/T_1$, a marked increase in the acoustic ringing was observed at all field values, mostly when $\mathbf{H} \parallel c$. Now we will only briefly comment on this, since this effect will be the subject of a future work. We notice that a strong ringing was observed in Fe-doped 2H-NbSe_2 as well,¹⁸ in the proximity of the spin-glass phase transition. We argue that if a glass-phase transition occurred the vortices, that in the liquid phase are free to move reversibly, would transfer their elastic energy to the lattice (via the pinning mechanism). The comparison with the spin-glass system can be understood if we assume that a coupling between the spin fluctuations and the phonons is also playing a role.

Furthermore, when studying layered superconductors, it is necessary to deal with the dimensionality crossover that might occur in the FLL. The crossover field B_{cr} was calculated by L. I. Glazman and A. E. Koshelev. In the limit $\lambda_c < \lambda_{ab}^2/s$, with λ_c and λ_{ab} the London penetration depth for $H \perp c$ and $H \parallel c$, respectively, namely when the Josephson coupling dominates over the magnetic coupling, one can write^{19,20}

$$B_{cr} \simeq 2\pi \frac{\Phi_0}{\gamma^2 s^2} \log(s\gamma/\xi_{ab}) \sim \frac{\Phi_0}{\gamma^2 s^2}, \quad (3)$$

where s is the inter-layer distance, Φ_0 is the quantum of magnetic flux, ξ is the coherence length. Since here $\gamma \sim 2$ we calculated a critical field of about 90 T, which implies that the FLL is in the 3D correlated regime, for all the applied fields. At such low fields the usual picture of "flux lines" can be restored.

Another important effect is due to the temperature. In 1991 R. J. Clem²¹ predicted a divergence of the root mean square amplitude of the fluctuations, for an isolated vortex line, given by a stack of 2D pancakes, in absence of the inter-layer Josephson coupling, at the temperature

$$T_{cr} = \frac{\Phi_0^2 s}{32\pi^2 k_B \lambda_{\parallel}(T)^2}. \quad (4)$$

When the vortices density is large enough that an array of flux lines enters into the system, the thermal energy can still decouple the vortices in different layers. The new crossover temperature T'_{cr} depends on the field, but in the $H \rightarrow 0$ limit, the equivalence $T'_{cr} = T_{cr}$ is restored. T_{cr} was identified by Clem^{21,22} with the Kosterlitz-Thouless transition temperature. This crossover was studied in the cuprates by employing μSR ,²³ and NMR²⁴. We calculated that for our compound $T_{cr} \sim 17$ K, by taking into account the temperature dependence of London penetration depth λ .

As far as the peak in the $1/T_1$ is concerned, we started our analysis with a BPP-like relation for the spectral density of the spin fluctuations.²⁵ As shown in Ref. 15 $1/T_1$ due to vortex motions can be written in the form¹⁵:

$$\frac{1}{T_1} = \frac{(\gamma^5)^2}{2} \frac{\Phi_0^2 s^2}{4\pi\lambda_c^4} < u^2 >_{3D} \frac{1}{\xi_{ab}^2} \frac{1}{l_e^2 \sqrt{3}} \tau_c(T, H) \ln \left[\frac{\tau_c(T, H)^{-2} + \omega_L^2}{\omega_L^2} \right], \quad (5)$$

where γ^5 is the As gyromagnetic ratio and $< u^2 >_{3D}$ the root mean-squared amplitude of the local field fluctuations when the vortex lattice is correlated along the c -axis.¹⁹ l_e is the inter-vortex spacing, τ_c is the correlation time, which depends on the dynamics involved in the fluctuations, and ω_L is the Larmor frequency. We firstly assumed that τ_c had an Arrhenius-like form, as claimed in $\text{YBa}_2\text{Cu}_4\text{O}_8$ ¹⁵ and $\text{HgBa}_2\text{CuO}_{4-\delta}$ ²⁶ cuprates, where a collective activated motion is thought to describe the dynamics acting in the FLL:

$$\tau_c(T, H) = \tau_0 \exp \left(\frac{U(H)}{T} \right). \quad (6)$$

By using the above equation to analyze BaFeRAs data, we obtained non-physical results for the intra-valley correlation time τ_0 (10^{-22} s). An anomalous value of τ_0 was firstly observed in our previous work.¹²

We then considered the VTF law (Fig. 4), employed to describe the divergence of the relaxation time in a glass-forming system:

$$\tau_c(T, H) = \tau_0 \exp \left(\frac{U_{eff}(H)}{T - T_0(H)} \right), \quad (7)$$

where U_{eff} refers an effective energy barrier and T_0 is the temperature where the divergence occurs.²⁷⁻³⁰ This interpretation was suggested by the theoretical prediction of Fisher et al.³ In this case a divergence of the viscosity η can be related to the divergence of the correlation time $\eta = \tau G_\infty$, where G_∞ is the high frequency shear modulus. With this correction the fit gives more meaningful values for the intra-valley correlation times τ_0 .

To test the validity of this approach we employed the VTF law to fit the peak in $1/T_1$ in the cuprates (Fig. 5) and we obtained quite nice results for the lowest fields. However, in this case also the Arrhenius law gave good results, so it is not easy to distinguish between the two scenarios. We recall that the Arrhenius law is employed to describe the divergence of the viscosity in glass-forming systems, like silica, which are called "strong" systems, whereas the VTF law is rather employed to describe the "fragile" systems.³¹ The terminology "fragile" and "strong" refers to the extent in which the temperature dependence of the viscosity deviates from Arrhenius behavior: the fragility m of glass-forming systems reflects the slope (i.e. logarithmic derivative) of the viscosity of a material with temperature, as it approaches the glass transition temperature:

$$m = \frac{\partial(\ln(\tau))}{\partial(T_g/T)}, \quad (8)$$

where τ is the relaxation time and the derivative is evaluated at $T = T_g$. We further comment on the width of

the peaks in the cuprates by observing that the sample was an oriented powder, instead of single crystal, where a distribution of correlation times might have broadened the peak.




FIG. 4. The figure shows the spin-lattice relaxation rates, at 3 T (green circles), 7 T (blue squares), 8.5 T (black diamonds), for $\mathbf{H} \parallel c$. The electronic contribution has been subtracted from the raw data. The red lines are the best fits, according to Eq.s 5 and 7.

A second approach to describe the glass-phase transition is the dynamical scaling. The vortex-glass correlation length ξ_{DS} , which is the length scale over which the phase of the pair wavefunction is correlated, and the characteristic relaxation time τ_{DS} both diverge at the glass transition:^{27,28}

$$\tau_{DS}(T, H) \sim |\epsilon|^{-\beta} \quad (9)$$

$$\epsilon = \frac{T - T_g(H)}{T}, \quad (10)$$

where T_g is the glass-phase transition temperature and β the corresponding critical exponent, and ϵ the reduced temperature. In Table I we present the fitting values, with their error bars, for both the VTF law and the power-law fitting parameters. We notice that the glass phase transition temperature T_g is in good agreement with the instability temperature T_0 , extracted by the VTF law. In addition, the β exponent agrees with the predicted universality class for 3D systems, where it is expected to be 6 ± 1 .²⁷

If we collect these results in a phase diagram (Fig. 6), we notice that the "instability-line" intercepts the temperatures axis near $T_{cr} \sim 17$ K, which marks a crossover between a regime where the vortices are correlated and a




FIG. 5. The figure shows the spin-lattice relaxation rates data, at 5.9 T (green diamonds), 9.4 T (blue squares) and 14.9 T (black circles) in YBCO124, when $\mathbf{H} \parallel c$. The electronic contribution has been subtracted from the raw data. The data in the figure are taken from Ref. 32, whereas the red lines correspond to a fit using a correlation time described by a VTF law. For the case of 5.9 T and 9.4 T the fit quality is satisfactory, while this is not the case for the highest field (14.9 T) measurement (see text).

high temperature one, where they are uncorrelated. Furthermore the fitting results and the peak widths appear to be in agreement with a liquid-glassy phase transition rather than with a first order transition. We stress that the line connecting the position of the peak in the $1/T_1$ doesn't mark any phase boundary, but on the other hand it marks the temperature at which the correlation time matches the inverse of the Larmor frequency, leading to an enhancement of the spectral density of the transverse field fluctuations.

H (T)	$U_{\text{eff}}(\text{K})$	$T_0(\text{K})$	$T_g(\text{K})$	β
3 T	22.4 ± 12.4	16 ± 1.6	16.5 ± 0.3	5.9 ± 0.4
7 T	19.7 ± 3	15 ± 0.4	15.5 ± 0.5	6.3 ± 0.9
8.5 T	16.9 ± 4.9	14.5 ± 0.6	15 ± 0.2	5.8 ± 0.3

TABLE I. The table presents the fitting values, for the VTF law and the dynamical scaling approach. In both cases τ_0 is about 10^{-13} s, as expected for the correlation time for the vortex intra-valley motion.¹⁰ Similar time values have been recently obtained by ac-susceptibility measurement on the Co-doped member of the same family of iron-pnictides⁹.

Let us now comment on the height of the peaks: both the cuprate and the pnictide show an increasing amplitude of the $1/T_1$ peak around 35 K, for YBCO124, and around 17 K, for BaFeRAs. This particular temperature coincides with T_{cr} for both cases. This may explain the behavior of such peaks with the magnetic field:




FIG. 6. The equilibrium phase diagram ($j = 0$) for the vortex lattice. The black squares show the upper critical field H_{c2} line, measured by SQUID magnetometry. The red solid line is a guide to the eye. The black circles refer to the peak in the spin-lattice relaxation rate. The green dotted line is an guide to the eye which does not mark any phase boundary (see text). The blue half full circles mark the instability temperature T_0 , in agreement with the VTF law and the blue arrow marks T_{cr} . The blue solid line is a guide to the eye. The dimensional crossover field B_m^{2D} is marked with an arrow, because it is expected at very high fields.

by applying higher fields, the peaks move towards lower temperatures, so that the correlation time, and accordingly the spin-lattice relaxation rate, are strongly affected by the VTF law, via equation 5. We further observe that the glassy-phase transition temperature at zero field, $T_0(0) \approx T_g(0)$, is expected below T_c , as observed in the cuprates.^{4,5} Remarkably, this glass-transition temperature is found very close to the Kosterlitz-Thouless temperature. The same result was also found in the cuprates, where $T_{cr} \sim 35$ K.

IV. CONCLUSIONS

This work completes a previous NMR study on a superconductor belonging to the 122 family of iron-based superconductors. We investigated the fluctuations of local fields and we interpreted them in terms of the vortex dynamics. We have studied how the magnetic field intensity affects the peak in the spin-lattice relaxation rate $1/T_1$, and we found that this behavior is consistent with a liquid-glassy phase transition occurring in the vortex lattice. Our results are compared with the ones for the YBCO124 cuprate, where similar peaks were found. Information on the scaling exponents for the dynamics and on the correlation time was obtained and shown to be consistent with a 3D vortex lattice model.

ACKNOWLEDGEMENTS

We acknowledge H. Mayaffre and M.-H. Julien of LNCMI-Grenoble. This work was supported by Fondazione Cariplo (research grant n.2011-0266) and by European Commission through the EuroMagNET II network (Contract No. 228043). Work done in Ames Lab

(PCC and AT) was supported by the U.S. Department of Energy, Office of Basic Energy Science, Division of Materials Sciences and Engineering. The research was performed at the Ames Laboratory. Ames Laboratory is operated for the U.S. Department of Energy by Iowa State University under Contract No. DE-AC02-07CH11358.

-
- ¹ Y. Kamihara, T. Watanabe, M. Hirano, and H. Hosono, J. Am. Chem. Soc. **130**, 3296-3297 (2008).
 - ² N. Ni, M. E. Tillman, J.-Q. Yan, A. Kracher, S. T. Hannahs, S. L. Bud'ko, and P. C. Canfield, Phys. Rev. B **78**, 214515 (2008).
 - ³ M. P. A. Fisher and D. H. Lee, Phys. Rev. B **39**, 2756 (1989).
 - ⁴ D. A. Huse, M. P. A. Fisher and D. S. Fisher, Nature **358**, 553 (1992).
 - ⁵ P. L. Gammel, L. F. Schneemeyer, J. V. Waszczak, and D. J. Bishop, Phys. Rev. Lett. **61**, 1666 (1988).
 - ⁶ A. Reyes, X. P. Tang, H. N. Bachman, and W. P. Halperin, J. A. Martindale and P. C. Hammel, Phys. Rev. B (R) **55**, 737 (1997).
 - ⁷ N. J. Curro, C. Milling, J. Haase and C. P. Slichter, Phys. Rev. B **62**, 3473 (2000).
 - ⁸ R. H. Koch, V. Foglietti, W. J. Gallagher, G. Koren, A. Gupta, and M. P. A. Fisher, Phys. Rev. Lett. **63**, 1511 (1989).
 - ⁹ G. Prando, M. Abdel-Hafiez, S. Aswartham, A.U.B. Wolter, S. Wurmehl, and B. Buchner, arXiv:1207.2457v1.
 - ¹⁰ G. Blatter, M. Y. Feigel'man, Y. B. Geshkenbein, A. I. Larkin, V. M. Vinokur, Rev. Mod. Phys. **66**, 1125 (1994).
 - ¹¹ G. Carneiro, Phys. Rev. B **45**, 2391 (1992).
 - ¹² L. Bossoni, P. Carretta, A. Thaler and P. C. Canfield, Phys. Rev. B **85**, 104525 (2012).
 - ¹³ D. A. Torchetti, M. Fu, D. C. Christensen, K. J. Nelson, T. Imai, H. C. Lei, and C. Petrovic, Phys. Rev. B **83**, 104508 (2011).
 - ¹⁴ D. Parker, O. V. Dolgov, M. M. Korshunov, A. A. Golubov, and I. I. Mazin, Phys. Rev. B **78**, 134524 (2008).
 - ¹⁵ M. Corti, J. Suh, F. Tabak, A. Rigamonti, F. Borsa, M. Xu, B. Dabrowski, Phys. Rev. B **54**, 9469 (1996).
 - ¹⁶ D. Majer, E. Zeldov, and M. Konczykowski, Phys. Rev. Lett. **75**, 1166 (1995).
 - ¹⁷ G. Blatter, V. Geshkenbein, A. Larkin and H. Nordborg, Phys. Rev. B **54**, 72 (1996).
 - ¹⁸ M. C. Chen and C. P. Slichter, Phys. Rev. B **27**, 278 (1983).
 - ¹⁹ L. I. Glazman and A. E. Koshelev, Phys. Rev. B **43**, 2835 (1991).
 - ²⁰ M. Tinkham, *Introduction to Superconductivity*, Second Edition, Dover (1996).
 - ²¹ J. R. Clem, Phys. Rev. B **43**, 7837 (1991).
 - ²² M. R. Beasley, J. E. Mooij, T. P. Orlando, Phys. Rev. Lett. **42**, 1165 (1979).
 - ²³ S. L. Lee, F. L. Pratt, S. J. Blundell, C. M. Aegerter, P. A. Pattenden, K. H. Chow, E. M. Forgan, T. Sasaki, W. Hayes, and H. Keller, Phys. Rev. Lett. **79**, 1563 (1997).
 - ²⁴ P. Carretta, Phys. Rev. B(R) **45**, 5760 (1992).
 - ²⁵ L. C. Hebel and C. P. Slichter, Phys. Rev. **113**, 1504 (1959).
 - ²⁶ B. J. Suh, F. Borsa, J. Sok, D. R. Torgeson, M. Corti, A. Rigamonti, and Q. Xiong, Phys. Rev. Lett. **76**, 1928 (1996).
 - ²⁷ J. Souletie, J Phys. France **51**, 883 (1990).
 - ²⁸ P. Taborek, R. N. Kleiman, and D. J. Bishop, Phys. Rev. B **34**, 1835 (1986).
 - ²⁹ P.G. Debenedetti and F.H. Stillinger, Nature **410**, 259 (2001).
 - ³⁰ F. Rao, A. Cristanti and F. Rotort, Europhys. Lett. **62**, 869 (2003).
 - ³¹ T. A. Vilgis, Phys. Rev. B **47**, 2882 (1993).
 - ³² A. Rigamonti, F. Borsa, P. Carretta, Rep. Prog. Phys. **61**, 1367-1439 (1998).